

## Sn63Pb37 Solder Alloy

### Product Description

Sn63Pb37 is one of the most common eutectic SnPb alloy used in different soldering processes before lead free implementation. SnPb alloy possess excellent wettability to various substrates and hence assures superior solderability. It can be used in dipping application. It is available in the forms of solder bars and solder wires.

### Alloy Composition

Main Composition		JIS Z 3282 (wt%)
Tin	Sn	63 +/- 0.5
Lead	Pb	Remainder
<b>Contamination</b>		
Antimony	Sb	0.20 max
Silver	Ag	0.10 max
Aluminium	Al	0.001 max
Arsenic	As	0.03 max
Bismuth	Bi	0.10 max
Cadmium	Cd	0.002 max
Copper	Cu	0.08 max
Iron	Fe	0.02 max
Indium	In	0.10 max
Nickel	Ni	0.01 max
Zinc	Zn	0.001 max

### Specification

Item	Result
Alloy Melting Temperature	183 °C
DSC at 5 °C/min	
Density	8.42 g/cm <sup>3</sup>
Water Displacement Method	
Surface Insulation Resistance	
(85°C, 85%RH, 168hrs)	> 1 x 10 <sup>8</sup> Ω, Pass
IPC-TM-650 2.6.3.3	> 1 x 10 <sup>11</sup> Ω, Pass
JIS Z 3197 8.5.3	Pass
Electromigration	
(85°C, 88.5%RH, 596hrs)	
IPC-TM-650 2.6.14.1	
Spread Factor	
JIS Z 3197 8.3.1.1	
245° C	> 80%
Wettability	
IPC-TM-650 2.4.14.2	
JIS Z 3197 8.3.1.2	
245° C	5.54 mN, 0.33 sec
Mechanical Properties (As-Cast)	
Instron Series IX Automated	
Materials Test System	
ASTM E8M (3 mm/min at 23 °C)	
Tensile Strength	55.41 MPa
Yield Strength	44.64 MPa
Max Percent Strain	62.15 %
Energy to Yield Point	0.17 J
Energy to Break Point	16.47 J
Toughness	20.07 MPa

### **Application**

Sn63Pb37 can be used for wave soldering, dipping, HASL and auto-topping processes. The operating temperature should be set >240 °C, depending on applications.

Conveyor speed can be set up to a maximum of 1.8 m/min for single-sided boards and recommended to set at between 1.2m/min to 1.6m/min for double-sided boards. Recommended preheat temperature is 90 – 120 °C on-board, dependent on flux activation temperature, machine design and board complexity.

### **Top-up Solder**

Sn63Pb37 is recommended as top-up solder.

### **Storage**

Store the solder bar in a cool, dry and non-corrosive environment. Wrap up the solder bar when not in use to reduce exposure to environment. Solder bar can be kept for 5 years if proper storage conditions are observed.

### **Health & Safety**

The product when use or handling maybe hazardous to health or environment. Please refer to Material Safety Data Sheet for more information.

### **Packaging**

Solder Bar: 25kg per box, Solid Wire: 20kg per roll. For any other packing requirements, please refer to the sales department.

#### DISCLAIMER OF LIABILITY

"All statements, information and recommendations contained in this catalog are based on data and test results which we consider, to the best of our knowledge and belief, to be reliable and informative to the users but the accuracy and completeness thereof is not guaranteed. No warranty, expressed or implied, statutory or otherwise, is given regarding the use of the information and products contained in this catalog since the conditions and suitability for use, handlings, storage or possession of the products are determined by the users and are therefore beyond our control. We shall not be liable in respect of any liabilities, losses (including consequential losses), damages, proceedings, costs, claims or injuries whatsoever sustained or suffered by the users (including any third parties) in connection with the use of the information, recommendation and the products contained in this catalog."

### **Singapore Asahi Chemical and Solder Industries Pte Ltd**

47 Pandan Road Singapore 609288

Tel: +65 6262-1616 Fax: +65 6261-6311

Website: <http://www.asahisolder.com> Email: [enquiry@sinasahi.com.sg](mailto:enquiry@sinasahi.com.sg)