

SnCu0.2无铅焊料 添加焊料



介绍

SnCu0.2是SnCu0.7的添加焊料。

应用

SnCu0.2能用于波峰焊, 浸焊和HASL。焊接操作温度要根据SnCu0.7合金具体的应用而定。

存储

将焊棒储存在凉爽、干燥和无腐蚀性的环境中。不使用时将焊棒包装好。在合适的储存环境中储存, 焊棒可保存5年。

健康 & 安全

此产品在使用或操作时, 或许会危害健康和环境。更多信息, 请参考材料安全数据。

包装

焊棒: 25kg每箱, 焊丝: 20kg每箱(直径: 0.25, 0.3, 0.4, 0.5, 0.6, 0.8, 1.0, 1.2, 1.6, 2.0 和 3.0 mm)。如果有其他包装需求, 请与销售部门联系。

产品特性

测试

合金熔点温度 227 - 231°C

DSC at 5°C/min

密度 7.30 g/cm³

Water Displacement Method

测试成绩

合金组成

主要成分		Asahi Specs (wt%)	
锡	Sn	余量	
铜	Cu	0.2 +/- 0.1	
杂质			
银	Ag	0.10	max
铝	Al	0.005	max
砷	As	0.03	max
铋	Bi	0.10	max
镉	Cd	0.002	max
铁	Fe	0.02	max
铟	In	0.10	max
镍	Ni	0.01	max
铅	Pb	0.05	max
锑	Sb	0.05	max
锌	Zn	0.002	max

DISCLAIMER OF LIABILITY

"All statements, information and recommendations contained in this catalog are based on data and test results which we consider, to the best of our knowledge and belief, to be reliable and informative to the users but the accuracy and completeness thereof is not guaranteed. No warranty, expressed or implied, statutory or otherwise, is given regarding the use of the information and products contained in this catalog since the conditions and suitability for use, handlings, storage or possession of the products are determined by the users and are therefore beyond our control. We shall not be liable in respect of any liabilities, losses (including consequential losses), damages, proceedings, costs, claims or injuries whatsoever sustained or suffered by the users (including any third parties) in connection with the use of the information, recommendation and the products contained in this catalog."

Singapore Asahi Chemical and Solder Industries Pte Ltd

47 Pandan Road Singapore 609288

Tel: +65 6262-1616 Fax: +65 6261-6311

Website: <http://www.asahisolder.com> Email: enquiry@sinasahi.com.sg