



T-9A

*Inorganic Hot Tinning
Water Soluble Liquid Flux*

Product Description

T-9A is an inorganic acid flux. It is a fumeless and non-flammable aqueous solution designed to restore the solderability of tarnished copper surface especially for hot solder tinning process for copper wire operations. The flux residue can be completely removed with thorough water rinse providing copper wire surface free from ionic contamination.

Application

The copper wire is first applied through the flux pot which contains T-9A. After fluxing, no pre-heating is required and the surface of the copper wire is cleaned by passing the wire through a wet cloth before wire is conveyed through the bath of molten solder.

Residue Removal

The residue left after soldering is hygroscopic and ionisable. Complete residue removal immediately after soldering is recommended. Removal of the residue can best be achieved with water at a minimum temperature of 40°C, followed by a final deionised water rinse.

Recommended Solvent

No solvent is required.

Health and Safety

Observe standard precautions for handling and use, such as well-ventilated areas and avoidance of prolonged or repeated contact with the skin. For more information, please refer to the Material Safety Data Sheet.

Storage

Under proper storage condition, T-9A can be stored for about 6 months.

Packaging

Available in 25kg/carboy.

Specification

Item	Result
State	Liquid
Colour	Colourless
Specific Gravity @ 25°C	1.051 +/- 0.005
<small>JIS Z 3197 8.2.2</small>	
Non-volatile Solid Content (110°C, 3hr)	5.1 +/- 0.3 wt%
<small>IPC-TM-650 2.3.34</small>	
<small>JIS Z 3197 8.1.3</small>	
Halide Content	4.2 +/- 0.2 wt%
<small>JIS Z 3197 8.1.4.2.1</small>	
Copper Corrosion Test	Pass
<small>IPC-TM-650 2.6.15</small>	
<small>JIS Z 3197 8.4.1</small>	
pH	<1
Flash Point	None
Spread Factor	> 85% (SnPb)
<small>JIS Z 3197 8.3.1.1</small>	
Surface Finish	Shiny

DISCLAIMER OF LIABILITY

"All statements, information and recommendations contained in this catalog are based on data and test results which we consider, to the best of our knowledge and belief, to be reliable and informative to the users but the accuracy and completeness thereof is not guaranteed. No warranty, expressed or implied, statutory or otherwise, is given regarding the use of the information and products contained in this catalog since the conditions and suitability for use, handlings, storage or possession of the products are determined by the users and are therefore beyond our control. We shall not be liable in respect of any liabilities, losses (including consequential losses), damages, proceedings, costs, claims or injuries whatsoever sustained or suffered by the users (including any third parties) in connection with the use of the information, recommendation and the products contained in this catalog."

Singapore Asahi Chemical and Solder Industries Pte Ltd

47 Pandan Road Singapore 609288

Tel: +65 6262-1616 Fax: +65 6261-6311

Website: <http://www.asahisolder.com> Email: enquiry@sinasahi.com.sg