

V349 CLF5043

No Clean Core Wire

Fine Wire Application



Product Description

Viromet* 349, with a composition of Sn/Ag4.1/Cu0.5/In4.0, is one of the high-performance lead free solder available in the industry. Viromet 347 core wire can be used as a drop-in replacement for conventional Sn/Pb solders in manual soldering. It possesses superior mechanical properties and better reliability as compared to conventional Sn/Pb solders.

V349 CLF5043 lead free no clean core flux solder wire is formulated using purest raw chemicals together with halide-free materials, which guarantees absolute flux core continuity and consistency in solder properties. It provides excellent instant wetting action and superior solderability on a variety of surface finishes.

This wire is specially formulated for fine wire applications, e.g. 0.4 mm and below.

Application

V349 CLF5043 lead free no clean core flux solder wire is easy to use for automatic, manual, rework, point and brush soldering. For the best soldering results, the recommended parameters are shown:

Solder Iron Tips:	All Types especially the tapered types
Soldering Temp:	330 - 380 °C
Soldering Time:	1 - 3 secs

- Keep solder iron tips clean.
- Tinned iron tips before use.
- Wear gloves when soldering to avoid contaminating the wire.

(Note: Soldering parameters are dependent on tip type, soldering station wattage configuration, wire diameter and type of applications.)

Specification

Item	Result
Alloy Composition	Sn/Ag4.1/Cu0.5/In4.0
Flux Content	3.0 ± 0.3 wt%
Density of Core Flux @ 25°C	1.066
Halide Content	Not added
<small>JIS Z 3197 8.1.4.2.1</small>	
Water Extract Resistivity	> 1 x 10 ⁴ Ω-cm
<small>JIS Z 3197 8.1.1</small>	
Surface Insulation Resistance (85°C, 85%RH, 168hrs)	> 1 x 10 ⁸ Ω, Pass
<small>IPC-TM-650 2.6.3.3</small>	
<small>JIS Z 3197 8.5.3</small>	> 1 x 10 ¹¹ Ω, Pass
Electromigration (85°C, 88.5%RH, 596hrs)	Pass
<small>IPC-TM-650 2.6.14.1</small>	
Copper Corrosion Test	Pass
<small>IPC-TM-650 2.6.15</small>	
<small>JIS Z 3197 8.4.1</small>	
Copper Mirror Test	Classified as "M", Pass
<small>IPC-TM-650 2.3.32</small>	
<small>JIS Z 3197 8.4.2</small>	
Flux Activity Classification	ROM0
<small>IPC J-STD-004</small>	
Spread Factor	> 80% (V349)
<small>JIS Z 3197 8.3.1.1</small>	
Residue Dryness Test	Dry
<small>JIS Z 3197 8.5.1</small>	
Residue Appearance	Light Yellowish & Minimal

* World Patent No. 03/006200 A1

* US Patent No. 5,985,212; 6,176,947; 6,843,862

V349 CLF5043 No Clean Core Wire

PHYSICAL PROPERTIES

Melting Temperature	205 - 210 °C
Coefficient of Thermal Expansion	22.9 μm/m°C
Density	7.40 g/cm ³

MECHANICAL PROPERTIES (As-Cast) (ASTM E8M 3mm/min at 23°C)

Tensile Strength	72.03 MPa
Yield Strength	52.98 MPa
Young's Modulus	5.95 GPa

RESIDUAL REMOVAL

Since the residues are light yellowish, minimal, dry, non-tacky and practically inert after soldering, removal is usually not necessary. For assemblies that require cleaning, the residue of V349 CLF5043 lead free no clean core flux solder wire can be completely removed by any solvent type flux cleaner available in the market.

STORAGE

Store the solder wire in a cool, dry and non-corrosive environment. Wrap up the solder wire when not in use to reduce exposure to environment. V349 CLF5043 lead free no clean core flux solder wire can be kept for 2 years if proper storage conditions are observed.

HEALTH and SAFETY

Wear a chemical mask if the operators are allergic to the fumes released during soldering. For more information, please refer to Material Safety Data Sheet.

PACKAGING

V349 CLF5043 lead free no clean core flux solder wire is commonly available in various diameters such as 0.25, 0.3 and 0.4 mm.

Packaging	0.20kg	0.20kg	0.20kg	Fat Bobbin (for autosoldering)	0.03kg	0.10kg	0.20kg
Diameter (mm)	0.25	0.3	0.4	Diameter (mm)	0.25	0.3	0.4

DISCLAIMER OF LIABILITY

"All statements, information and recommendations contained in this catalog are based on data and test results which we consider, to the best of our knowledge and belief, to be reliable and informative to the users but the accuracy and completeness thereof is not guaranteed. No warranty, expressed or implied, statutory or otherwise, is given regarding the use of the information and products contained in this catalog since the conditions and suitability for use, handlings, storage or possession of the products are determined by the users and are therefore beyond our control. We shall not be liable in respect of any liabilities, losses (including consequential losses), damages, proceedings, costs, claims or injuries whatsoever sustained or suffered by the users (including any third parties) in connection with the use of the information, recommendation and the products contained in this catalog."

Singapore Asahi Chemical and Solder Industries Pte Ltd
 47 Pandan Road Singapore 609288
 Tel: +65 6262-1616 Fax: +65 6261-6311
 Website: <http://www.asahisolder.com> Email: enquiry@sinasahi.com.sg