

FX-880*Flux Remover***Product Description**

Hasaconi Flux Remover FX-880 is specially developed to remove all types of rosin and resin flux residues, oils and grease from soldering connections. FX-880 exhibits superior cleaning ability and provides fast and excellent cleaning action, being more effective than denatured alcohol. FX-880 is formulated using non-CFC chemicals and therefore do not cause pollution to our environment.

Application

FX-880 is very suitable for ultrasonic, dipping and spraying cleaning process where residues can be cleaned thoroughly.

Uses

If dipping washing process is employed, the liquid should be replaced at adequate intervals in order to avoid solvent contamination.

Specification

| Item | Result |
|-------------------------|----------------------|
| State | Low viscosity liquid |
| Color | Colorless |
| Specific Gravity @ 25°C | 0.940 +/- 0.005 |
| Boiling Point | 56°C |
| Flash Point | 52°C |

Health and Safety

This cleaner consist of at least 80% of aliphatic alcohol and <20% of organic chloride and some proprietary additives from Asahi. The chemicals are safe to be used in the production line, as all the chemicals used are non-toxic. In order to avoid any allergy problems, wear proper gloves and safety gloves during handling to avoid any contacts with our skin and eyes.

Storage

Keep FX-880 in a cool and well-ventilated environment. Under proper storage conditions, FX-880 can be stored for up to 6 months.

Packaging

Available in 17kg/carboy.

DISCLAIMER OF LIABILITY

"All statements, information and recommendations contained in this catalog are based on data and test results which we consider, to the best of our knowledge and belief, to be reliable and informative to the users but the accuracy and completeness thereof is not guaranteed. No warranty, expressed or implied, statutory or otherwise, is given regarding the use of the information and products contained in this catalog since the conditions and suitability for use, handlings, storage or possession of the products are determined by the users and are therefore beyond our control. We shall not be liable in respect of any liabilities, losses (including consequential losses), damages, proceedings, costs, claims or injuries whatsoever sustained or suffered by the users (including any third parties) in connection with the use of the information, recommendation and the products contained in this catalog."

Singapore Asahi Chemical and Solder Industries Pte Ltd

47 Pandan Road Singapore 609288

Tel: +65 6262-1616 Fax: +65 6261-6311

Website: <http://www.asahisolder.com> Email: enquiry@sinasahi.com.sg